



Component - Plastics

File Number: E162823

FORMOSA CHEMICALS & FIBRE CORP PLASTICS DIV

201 TUNG HWA N RD
TAIPEI, 105 Taiwan

TAIRIPRO: K1525

Polypropylene (PP), pellets



Flammability	Value	Test Method
Flame Rating		
1.5 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
Electrical	Value	Test Method
Hot-wire Ignition (HWI)		UL 746
1.5 mm	PLC 3	
3.0 mm	PLC 2	
High Amp Arc Ignition (HAI)		UL 746
1.5 mm	PLC 0	
3.0 mm	PLC 0	
Comparative Tracking Index (CTI)	PLC 0	UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 0	UL 746
Arc Resistance	PLC 4	ASTM D495
Thermal	Value	Test Method
RTI Elec		UL 746
1.5 mm	65.0 °C	
3.0 mm	65.0 °C	
RTI Imp		UL 746
1.5 mm	65.0 °C	
3.0 mm	65.0 °C	
RTI Str		UL 746
1.5 mm	65.0 °C	
3.0 mm	65.0 °C	