

Typical property table

Polycarbonate resin TARFLON™ / TARFLON™

HQ2200



出光 IDEMITSU
Formosa Idemitsu Petrochemical Corporation (FIPC)

Clean PC with low-level contamination for high-quality film and printing applications.

Property	Method	Units	HQ2200
ISO identification mark	-	-	>PC<
Physical			
MFR	ISO 1133	g/10min	11
Density	ISO 1183	g/cm ³	1.2
Water absorption (50%RH 24hr)	ISO 62	%	0.23
Mechanical			
Tensile stress at Yield	ISO 527-1,2	MPa	65
Tensile strain at break	ISO 527-1,2	%	95
Flexural strength	ISO 178	MPa	90
Flexural modulus	ISO 178	GPa	2.3
Charpy impact strength(Notched)	ISO 179-1	kJ/m ²	80
Rockwell hardness	ISO 2039-2	R/M scale	R120/M50
Thermal			
Heat deflection temperature (1.8 MPa)	ISO 75-1,2	°C	125
Linear thermal expansion coefficient	ISO 11359-2	x 10 ⁻⁵ /°C	6.5
Mold shrinkage	ASTM D955	%	0.5 ~ 0.7
Optical			
Total luminous transmittance	ISO 13468-1	%	85 ~ 90
Electrical			
Dielectric strength	IEC 60243-1	kV/mm	30
Volume resistivity	ASTM D257	Ω · cm	> 10 ¹⁶
Dielectric Constant (1 MHz)	IEC 60250	-	2.85
Dielectric dissipation factor (1 MHz)	IEC 60250	-	0.0092
UL rating			
Flammability	UL94	(Class)	-
CTI	UL746A	(PLC level)	-
RTI (Elec)	UL746B	°C	-
RTI (Imp)	UL746B	°C	-
RTI (Str)	UL746B	°C	-
UV, water exposure or immersion	UL746C	-	-
Standard molding parameters			
Pre-drying condition	-	-	120 °C, 5~8hours
Cylinder & Die temperature	-	-	240 ~ 290 °C
Roll temperature	-	-	120 ~ 145°C

The above typical data are supplied only for technical information, not guaranteed values.
This document may be revised without prior notice.

rev. 2019.3.13