

Typical property table

Polycarbonate resin TARFLON™ / TARFLON™

## LC1500



出光 IDEMITSU

Formosa Idemitsu Petrochemical Corporation (FIPC)

Light-conduct PC with high-flow and low-level contamination for light guide panel and daytime running light.

Property	Method	Units	LC1500
ISO identification mark	-	-	>PC<
<b>Physical</b>			
MFR	ISO 1133	g/10min	65
Density	ISO 1183	g/cm <sup>3</sup>	1.2
Water absorption (50%RH 24hr)	ISO 62	%	0.23
<b>Mechanical</b>			
Tensile stress at Yield	ISO 527-1,2	MPa	65
Tensile strain at break	ISO 527-1,2	%	80
Flexural strength	ISO 178	MPa	90
Flexural modulus	ISO 178	GPa	2.3
Charpy impact strength(Notched)	ISO 179-1	kJ/m <sup>2</sup>	15
Rockwell hardness	ISO 2039-2	R/M scale	R120/M50
<b>Thermal</b>			
Heat deflection temperature (1.8 MPa)	ISO 75-1,2	°C	127
Linear thermal expansion coefficient	ISO 11359-2	x 10 <sup>-5</sup> /°C	6.5
Mold shrinkage	ASTM D955	%	0.5 ~ 0.7
<b>Optical</b>			
Total luminous transmittance	ISO 13468-1	%	90
<b>Electrical</b>			
Dielectric strength	IEC 60243-1	kV/mm	-
Volume resistivity	ASTM D257	Ω •cm	-
Dielectric Constant (1 MHz)	IEC 60250	-	-
Dielectric dissipation factor (1 MHz)	IEC 60250	-	-
<b>UL rating</b>			
Flammability	UL94	(Class)	V-2 (0.42 ~ 1.5 mm)
CTI	UL746A	(PLC level)	-
RTI (Elec)	UL746B	°C	80
RTI (Imp)	UL746B	°C	80
RTI (Str)	UL746B	°C	80
UV, water exposure or immersion	UL746C	-	-
<b>Standard molding parameters</b>			
Pre-drying condition	-	-	120 °C, 5~8hours
Cylinder temperature	-	-	240 ~ 260 °C
Mold temperature	-	-	80 ~ 120 °C

UL file No. QMFZ2.E238753

The above typical data are supplied only for technical information, not guaranteed values.  
This document may be revised without prior notice.

rev. 2019.3.13