

TAIRIREX<sup>®</sup> PS Resin

Property	Unit	Test Method	Test Condition	High Impact grade PS
				MP6500
Tensile Strength	kg/cm <sup>2</sup> (Mpa)	ASTM D-638 ( ISO 527 )	23 °C	270 (-)
Tensile Modulus	kg/cm <sup>2</sup> X10 <sup>4</sup> (MPa)	ASTM D-638 ( ISO 527 )	23 °C	16000 (-)
Tensile Elongation	%	ASTM D-638 ( ISO 527 )	23 °C	35 (-)
Flexural Strength	kg/cm <sup>2</sup> (Mpa)	ASTM D-790 ( ISO 178 )	23 °C	550 (-)
Flexural Modulus	kg/cm <sup>2</sup> X10 <sup>4</sup> (MPa)	ASTM D-790 ( ISO 178 )	23 °C	24000 (-)
Izod Impact Strength	kg-cm/cm (J/m)	ASTM D-256 (ISO 180)	23 °C 1/4" bar	7 (-)
Vicat Softening Point	°C	ASTM D-1525 (ISO 306B)	Annealed 80°C × 2hr 1/8" bar	98 (98)
Heat Deflection Temperature	°C	ASTM D-648 (ISO 75/A)	Annealed 80°C × 2hr 1/8" bar	87 (-)
Melt Flow Index		ASTM D-1238 (ISO 1113)	200°C X 5Kg (49N)	7
Specific Gravity		ASTM D-792 (ISO 1183)	23°C/23°C	1.04
Molding Shrinkage	%	ASTM D-955	3.2mm	0.4~0.7
Reidual Monomer	ppm max.			500
Flammability		UL-94	File No. E162823	1.5mm HB All Color
CHARACTERISTICS	Medium impact			

All tests were run under laboratory conditions, ASTM, ISO testing procedures. The data are intended as a general guide only.

**Formosa Chemicals Industries (Ningbo) Co., Ltd.**

TEL: (0574) 86028116/86028186 / FAX: (0574) 86029999-2116/2186

Address: FPG Ningbo Industrial Park Beliu Ningbo, China

Website: <https://en.fcfc-plastics.com/>

