


FORMOSA CHEMICALS & FIBRE CORPORATION
TAIRILITE® PC Resin

Property	Unit	Test Method	Test Condition	Self Extinguishing
				AC3830
Tensile Strength	kg/cm ² (MPa)	ASTM D-638	23 °C	710 (70)
Flexural Strength	kg/cm ² (MPa)	ASTM D-790	23 °C	1,010 (100)
Flexural Modulus	kg/cm ² (MPa)	ASTM D-790	23 °C	20,800 (2,040)
Rockwell Hardness	R-scale	ASTM D-785	23 °C	122
Izod Impact Strength	kg-cm/cm (J/m)	ASTM D-256	23 °C 1/8" bar	80 (785)
Heat Deflection Temperature	°C	ASTM D-648	Unannealed 18.6 kg/cm ² (1.8MPa) 1/8" bar	127
Melt Flow Index	g/10 min	ASTM D-1238	300°C × 1.2kg	5
Specific Gravity		ASTM D-792	23°C/23°C	1.2
Molding Shrinkage	%	ASTM D-955	3.2mm	0.5~0.7
Transmission	%	ASTM D-1003	Thickness (1.0mm)	-
Haze	%	ASTM D-1003	Thickness (1.0mm)	-
Flammability		UL-94	File No. E162823	1.0mm V-0 1.2mm V-0 1.5mm V-0 3.0mm V-0, 5VA All Color
Characteristics	Translucent, Flame retardant, Low flow, UV resistance,			

All tests were run under laboratory conditions, ASTM, ISO testing procedures. The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL: +886-2-27122211 / FAX: +886-2-27131649 /

Address: No.201, Dunhua N. Rd., Songshan Dist., Taipei City 105, Taiwan

Website: <https://en.fcfc-plastics.com/>

