



TAIRILITE® PC Resin

Property	Unit	Test Method	Test Condition	Self Extinguishing
				AC3900
Tensile Strength	kg/cm ² (MPa)	ASTM D-638	23 °C	610 (60)
Flexural Strength	kg/cm ² (MPa)	ASTM D-790	23 °C	1060 (104)
Flexural Modulus	kg/cm ² (MPa)	ASTM D-790	23 °C	24000 (2350)
Rockwell Hardness	R-scale	ASTM D-785	23 °C	R-121
Izod Impact Strength	kg-cm/cm (J/m)	ASTM D-256	23 °C 3.2mm	60 (500)
Charpy Impact Strength	KJ/m ²	ISO 179	23 °C 4mm	45
Heat Deflection Temperature	°C	ASTM D-648	Unannealed 18.6 kg/cm ² (1.8MPa) 1/8" bar	124
Vicat Softening Point	°C	ASTM D-1525	VICAT (10N)	146
Melt Flow Index	g/10 min	ASTM D-1238	300°Cx1.2kg	26
Specific Gravity		ASTM D-792	23°C/23°C	1.28
Molding Shrinkage	%	ASTM D-955	3.2mm	0.5-0.7
Flammability		UL-94	File No. E162823	1.5mm V-0 3.0mm V-0 NC
Characteristics	White color, Flame retardant, Cl, Br, Sb free			

All tests were run under laboratory conditions, ASTM, ISO testing procedures. The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL: +886-2-27122211 / FAX: +886-2-27131649 /

Address: No.201, Dunhua N. Rd., Songshan Dist., Taipei City 105, Taiwan

Website: <https://en.fcfc-plastics.com/>

